


Silver Nanoparticles, Reactant-Free

metals · inorganics · organometallics · catalysts · ligands · custom synthesis · cGMP facilities · nanomaterials

Silver Nanoparticles, (0.02mg/ml in 2mM sodium citrate) reactant free*

>99% Reactant Free*, in citrate buffer

| Cat. # | Description | λ max (nm) | Conc. |
|---------|-------------|--------------------|-----------|
| 47-0655 | 10nm | 390-400 | 0.02mg/ml |
| 47-0658 | 20nm | 405 | 0.02mg/ml |
| 47-0660 | 30nm | 410 | 0.02mg/ml |
| 47-0663 | 40nm | 416 | 0.02mg/ml |
| 47-0665 | 50nm | 425 | 0.02mg/ml |
| 47-0668 | 60nm | 430 | 0.02mg/ml |
| 47-0670 | 80nm | 457 | 0.02mg/ml |
| 47-0672 | 100nm | 490 | 0.02mg/ml |



*Reactant free – Less than 1% of reactants remaining from the manufacturing process.

Silver nanoparticles (0.02mg/ml in 2mM sodium citrate)

| Cat. # | Description | λ max (nm) | Conc. |
|---------|-------------|--------------------|-----------|
| 47-0620 | 10nm | 390-400 | 0.02mg/ml |
| 47-0623 | 20nm | 405 | 0.02mg/ml |
| 47-0626 | 30nm | 410 | 0.02mg/ml |
| 47-0630 | 40nm | 416 | 0.02mg/ml |
| 47-0633 | 50nm | 425 | 0.02mg/ml |
| 47-0635 | 60nm | 430 | 0.02mg/ml |
| 47-0638 | 80nm | 457 | 0.02mg/ml |
| 47-0640 | 100nm | 490 | 0.02mg/ml |

Description

Silver nanoparticles are an ideal alternative to gold nanoparticles due to their absorption maximum in the 400nm range, instead of 500nm for Gold Nanoparticles. Silver Nanoparticles retain the same protein and other ligand binding properties of Gold Nanoparticles.

Our silver nanoparticles are available in 8 different sizes ranging from 10-100nm, and are synthesized using a unique protocol. Our synthesis method produces monodisperse particles with a narrow and uniform size distribution (CV <13%).

Features

- Absorption maximum in the 400nm range.
- Readily bind proteins and other ligands for conjugate and sensor development.
- Unagglomerated monodisperse particles.
- Uniform shape and narrow size distribution (CV <13%).
- Low batch- to batch variation in size and shape.

Characteristics

Core diameter: Available from 10-100nm (Coefficient of Variance < 13%)

Concentration: 0.02mg/ml

Absorbance (λ max): 390-490nm

Supplied in 0.1mM Phosphate Buffered Saline (0.1X PBS). 10nm supplied in 2mM Sodium Citrate.

Storage/Stability

This product should be stored at 4°C in the dark. Do not freeze. If stored unopened and as specified, silver nanoparticles are stable for at least 6 months.

Precautions and Disclaimer

These products are for R&D use only, not for drug, household, or other uses. Please consult the Material Safety Data Sheet available online at www.strem.com for information regarding hazards and safe handling procedures.

Visit www.strem.com for new product information and searchable catalog.

Strem Chemicals, Inc.

7 Mulliken Way
Newburyport, MA 01950-4098
U.S.A.
Tel.: (978) 499-1600
Fax: (978) 465-3104
Email: info@strem.com

Strem Chemicals, Inc.

15, rue de l'Atome
Zone Industrielle
67800 BISCHHEIM France
Tel.: (33) 03 88 62 52 60
Fax: (33) 03 88 62 26 81
Email: info.europe@strem.com

Strem Chemicals, Inc.

Postfach 1215
77672 KEHL
Germany
Telefon: 0 78 51/ 7 58 79
Email: info.europe@strem.com

Strem Chemicals UK Ltd.

Newton Hall, Town Street
Newton, Cambridge
England CB22 7ZE
Tel.: 0845 643 7263
Fax: 0845 643 7362
Email: enquiries@strem.co.uk